

产品规格书

白色熔融氧化铝微粉

白色熔融氧化铝即白刚玉是以优质铝氧化粉为原料，经电熔提炼结晶而成，纯度高、自锐性好、耐酸碱腐蚀、耐高温、热态性能稳定它硬度略高于棕刚玉，韧性稍低，纯度高、自锐性好、磨削能力强、发热量小、效率高、耐酸碱腐蚀、耐高温热稳定性好。

化学成分

Al ₂ O ₃	Fe ₂ O ₃	Na ₂ O	MgO	K ₂ O	CaO	SiO ₂
≥99.35%	≤0.06%	≤0.30%	≤0.01%	≤0.03%	≤0.03%	≤0.06%

物理特性

莫氏硬度	比重	堆积密度	PH 值	耐火度
9.0	≥3.90g/cm ³	1.75-1.95g/cm ³	7.0	2100°C


磨料粒度组成标准

粒度	D3 (um)	D50 (um)	D94 (um)
F230	<82	53.0±3.0	>34
F240	<70	44.5±2.0	>28
F280	<59	36.5±1.5	>22
F320	<49	29.2±1.5	>16.5
F360	<40	22.8±1.5	>12
F400	<32	17.3±1.0	>8
F500	<25	12.8±1.0	>5
F600	<19	9.3±1.0	>3
F800	<14	6.5±1.0	>2
F1000	<10	4.5±0.8	>1
F1200	<7	3.0±0.5	>1 (at 80%)
F1500	<5	2.0±0.4	>0.8 (at 80%)
F2000	<3.5	1.2±0.3	>0.5 (at 80%)



主要用途:

- 喷砂 研磨 抛光等
- 陶瓷釉料, 地坪涂料添加剂等
- 磨刀石, 研磨石, 油石等制品的生产
- 抛光蜡, 抛光液, 胶粘剂等
- 纽扣, 手机壳, 擦银棒等抛光研磨液, 研磨剂等研磨介质
- 耐磨地坪, 耐磨胶粘剂, 耐磨层比如玻璃钢耐磨衬板等
- 陶瓷过滤板生产
- 陶瓷分离膜/陶瓷膜/陶瓷平板膜/平板式陶瓷膜/管式陶瓷膜/滤膜/膜组件
- 金刚石砂轮等, 金刚石工具干/水磨片, 树脂磨片等的生产
- 精密铸造代替锆粉
- 石材线条抛光轮等的生产



- 包装:** 25/20 公斤袋装
 25/20 公斤小袋+吨袋
 25/20 公斤小袋+托盘

